



# Perkadox<sup>®</sup> 16

when time matters

Nouryon

Perkadox<sup>®</sup>




## Curing at elevated temperature starts with Perkadox 16

- very stable in time
- long pot life time
- fast gel time

Perkadox 16 has the unique and ideal combination of high reactivity and a comfortable maximum recommended storage temperature of 20°C.

It is a solid peroxydicarbonate used for curing of unsaturated polyester and (meth)acrylic resins in the temperature range of 60°C and higher.

The high reactivity makes Perkadox 16 especially suitable for pultrusion and cured-in-place-pipe (CIPP) where fast gelation is needed. It is also a very suitable product to use in acrylic solid surface and in case a clear transparent end-product is required you may choose Perkadox 16S.



### Specifications

Appearance	white powder
Assay	94.0-97.0%
Inorganic + organic hydrolysable chloride	0.4% max.

### Characteristics

Density, 20°C	1.13 g/cm <sup>3</sup>
Bulk density, 20°C	450-480 kg/m <sup>3</sup>

For more information please check our website [nouryon.com](http://nouryon.com) or for contact details also.

**Your partner  
in essential solutions  
for a sustainable future**

**Nouryon**