## **Berol LS**

Berol® LS is an optimized surfactant-colloidal silica blend for degreasing, with anti-soiling benefits and no streaking

## **Specifications**

Appearance	Clear liquid at 20°C
Functional test	$\geq$ 35 (cloud point, 1% in water) °C
pH	5.5-8.5 (1% in water)

## Characteristics

Clear point	0°C
Density	9.2 lbs/gallon
Foam Height according to Ross-Miles	25°C, 0.05%: immediately 40 mm, after 5 min 35 mm
Pour point	-2 °C
Surface Tension according to Du Noüy, 25°C, 0.1% DIN 53914	29.6 mN/m
Viscosity	20 mPa.s (Sp2, 50 rpm, 20°C)
Solubility: Ethanol	Insoluble
Solubility: Isopropyl alcohol	Insoluble
Solubility: Low aromatic solvent	Insoluble
Solubility: Propylene glycol	Soluble
Solubility: Water	Soluble

Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Berol® is a registered trademark in many countries. For more information, please visit our website at www.nouryon.com.

