



CAS number

7631-86-9

Levasil® CB22 P is an alkaline, aqueous dispersion of colloidal silica that is approximately 40% solids by weight. The silica dispersion is sodium stabilized and the amorphous silica particles carry a negative surface charge. The silica particles are discrete, have a smooth, spherical shape, and are present in a narrow particle size distribution. The physical appearance of the dispersion is a translucent liquid, slightly more viscous than water. Levasil® CB22 P is produced for world-wide distribution.

Specification

Nouryon

Density at 20°C	1.289 - 1.304 g/cm ³
SiO ₂	39.2 - 40.8 wt%
pH at 20°C	9.2 - 10.2
Viscosity at 20°C	≤45 cP

Characteristics

Appearance/Color	Free of gelatinous and foreign matter. / No exceptional
	color variation.

Notes:

Nouryon's warranty and liability for non-conforming goods / products is limited solely to the elements set out in this specific section above, under the heading "Specification". This warranty is the sole warranty given by Nouryon. The other information included in this Product Data Sheet is not covered by Nouryon's warranty, and Nouryon will have no further obligation or liability with respect thereto.

Applications

Levasil® CB22 P is a specialty product designed primarily for hydraulically sealing geological formations and consolidation of soil and silt strata.

Storage

Levasil® CB22 P should be transported and stored at a temperature of 5-35°C (40-95°F). If the silica dispersion is allowed to freeze, the silica will irreversably precipitate. For bulk storage, the tank should be sealed and constructed of plastic, fiberglass reinforced plastic, or stainless steel. For packaged goods, any translucent packages should be stored out of direct sunlight or bright light. Under recommended conditions, Levasil® CB22 P has a shelf life of twelve months after production.

Packaging and transport

Levasil® CB22 P is available in bulk, 1000 liters IBC and 220 liters plastic drum.

Safety and handling

Before handling this material, review the corresponding Material Safety Data Sheet. Colloidal silica products are aqueous dispersions of amorphous silica. Colloidal silica is not classified as harmful, but as mildly irritating. Because the products can have a drying effect on the skin, protective gloves should always be used. In case of skin contact, wash the area of contact with plenty of water. The use of safety glasses is always recommended. In case of eye contact, rinse with large amounts of water and seek professional medical advice.

Certifications

ISO 9001 and 14001 certified.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Levasil® is a registered trademark of Nouryon Chemicals B.V. or affiliates in one or more territories

Contact Us

Europe, Middle East and Africa

Gothenburg and Cologne colloidal.silica@nouryon.com

South America

Jundiaí colloidal.silica@nouryon.com

North America

Houston colloidal.silica@nouryon.com

China Shanghai levasil.china@nouryon.com

North, South East Asia and Oceania

Taichung, Tokyo, Seoul and Singapore colloidal.silica@nouryon.com

India

Mumbai colloidal.silica@nouryon.com

